


VESTAMELT®

Thermoplastic copolyamide hotmelt adhesives

- **Paste dot**



Paste dot with rotary screen printing

Procedure

In the rotary screen printing process, an aqueous suspension of finely divided thermoplastic powder adhesives and additives, the paste, is pressed through the holes of a rotating, perforated cylinder, the screen stencil, onto a cold web of fabric. This procedure is particularly gentle to the substrate, and the wide range of options for formulating the paste grants the user flexibility in the application procedure. The process is characterized by high and economical coating rates ranging between 30 and 60 m/min. In particularly favorable cases, rates of 90 m/min have been attained. For these reasons, this application has surpassed the dry processes and now ranks first among powder applications (about 60%).

Application method

In the paste dot process, the aqueous adhesive dispersion is pumped through a hollow doctor blade into the interior of the rotating screen stencil. The viscosity of the paste can be adjusted to allow stencils of either course or fine screens to be used. The blade of the internal,

adjustable hollow doctor blade presses the paste through the holes of the stencil and onto the web of fabric, which is running over a counter-roller coated with hard or soft rubber. The paste dots are then dried, and circulating air or infrared radiators are next used to sinter the textile web.

In paste-dot coating, the blade system is of paramount importance because a perfect paste dot print pattern is expected to have the following properties:

- exact coat weight
- proper dot shape
- complete dot pattern
- no penetration of the fabric (strike through)

- **Composition**

A paste is an aqueous suspension consisting chiefly of the hotmelt adhesive powder and various additives that improve its properties. A typical paste contains the following ingredients:

- Water as the matrix
- Thickener for controlling the paste viscosity
- Dispersing agent to ensure that powder is uniformly distributed in the water
- Plasticizer to reduce the temperature of the joint and improve the joint's adhesion
- Wetting agent to improve adhesion: The wetting agent provides better wetting of hydrophobic surfaces.
- Slip additive/ flow enhancer for stabilizing the aqueous phase paste: The slip additive holds the water in the paste upon application; improvement of the dot geometry.
- Hotmelt adhesive powder

VESTAMELT® copolyamide standard grades

| VESTAMELT® | Properties, suitability |
|------------|---|
| 171-P1 | Paste additive for low viscosity grades, improves the resistance to strike back |
| 250-P1 | Good adhesion, high resistance to temperature, washing and steam, needs higher fusing temperatures |
| 350-P1 | Good resistance to temperature, multi-purpose standard adhesive for garments and industrial textiles |
| 430-P1 | Low melt viscosity, good resistance to steam, for pressure-sensitive and thermally sensitive face fabrics |
| 450-P1 | Low melting point, low fusing temperature, good resistance to strike back |
| 470-P1 | Low melting point, high melt viscosity, paste additive for low viscosity grades, improves the resistance to strike back |
| 640-P1 | Very low melting point for leather and furs, additive for grades with high melting point |
| 730-P1 | Low melting point, low melt viscosity, very good adhesion to surfaces that are difficult to fuse and to siliconized fabrics |
| 750-P1 | Good adhesion and good resistance to washing and dry cleaning, for light garments, decreased tack after coating |
| 755-P1 | Low melting point, high melt viscosity, good resistance to strike back, well adapted to substrates with polyester parts |
| 840-P1 | Medium melt viscosity, wide fusing range, high resistance to steam, multi-purpose applications in textiles |

VESTAMELT® copolyamide development grades

| VESTAMELT® | Properties, suitability |
|------------|---|
| X1027-P1 | Low melt viscosity, low fusing temperature, good resistance to steam, very good adhesion to surfaces that are difficult to fuse, well adapted to colored interlinings |
| X1310-P1 | Thermal cross-linkable hotmelt adhesive Before cross-linking: Low melting point and low melt viscosity, good adhesion to surfaces that are difficult to fuse After cross-linking: Increased resistance to temperature, washing, steam and dry cleaning |
| X1316-P1 | Thermal cross-linkable hotmelt adhesive Before cross-linking: High melting point and high melt viscosity After cross-linking: Very good resistance to temperature, washing, steam and dry cleaning |
| X1338-P1 | High melt viscosity, high resistance to steam, needs higher fusing temperatures, very good adhesion to surfaces that are difficult to fuse, well adapted to colored interlinings |

Particle sizes:
P1 = 0 bis 80 µm

This information and all further technical advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, Evonik disclaims all conditions and warranties, whether express or implied, including the implied warranties of fitness for a particular purpose or merchantability. Evonik shall not be responsible for consequential, indirect or incidental damages (including loss of profits) of any kind. Evonik reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

® = registered trademark

For more information please contact the following person:

Martin Risthaus

Phone + 49 2365 49-4356

martin.risthaus@evonik.com

Evonik Industries AG High Performance Polymers 45764 Marl Germany
Phone +49 2365 49-9878 www.vestamelt.com

